



PAN ASIA CHEMICAL CORPORATION

Tel:+886-2-2351-1212 Fax:+886-2-2396-2946

<http://www.pacc.com.tw> E-mail:paccsale@pacc.com.tw

## GLYCERINE POLYETHYLENE GLYCOL ETHER

Trade Name	Hydrophobic	EO mole	water% (max)	PH value (1% aq)	Color (30°C) alpha (max)	FORM in 25°C	OHV mg KOH/g	Applications產品應用範圍
TPEG 136	Glycerine	1	0.5	5.0-7.0	60	liquid	1200-1260	潤滑劑浸透劑 wetting agent ; penetrant
TPEG 590	Glycerine	11	0.5	5.5-7.5	60	liquid	286-294	
TPEG 900	Glycerine	18	0.5	5.0-7.0	60	liquid	183-192	
TPEG 990	Glycerine	20	0.25	5.5-7.5	60	liquid	174-182	
TPEG 990R	Glycerine	20	0.25	5.5-7.5	60	liquid	174-182	
TPEG 1100	Glycerine	23	0.8	5.5-7.5	60	liquid	146-160	

L = liquid S= solid L/S = liquid&amp;solid F= flake